

Other Views:
[INPADOC](#)

Title: **JP11268118A2: POLYOLEFIN POROUS FILM, PRODUCTION THEREOF, AND SEPARATOR FILM FOR BATTERY**

► [Want to see a more descriptive title highlighting what's new about this invention?](#)

Country: **JP** Japan
Kind: **A2** Document Laid open to Public inspection

Inventor(s): **HASHIMOTO AKINAO**
MORISHIGE KOZO
YAGI KAZUO

Applicant/Assignee:



MITSUI CHEM INC

[News, Profiles, Stocks and More about this company](#)

Issued/Filed Dates:

Oct. 5, 1999 / April 16, 1998

Application Number:

JP1998000106766

IPC Class:

B29C 55//28; B29C 35//08; B29C 67//20; H01M 2//16; //0C 8J/009/26; B29K 23//00; B29K 105//04; B29K 105//24; B29L 7//00;

Priority Number(s):

Jan. 26, 1998 JP1998000012711

Abstract:



Problem to be solved: To provide a film suitably used in a non-aqueous electrolyte and a separator for an electrolyte battery so as to have specific closing temp. and heat-resistant temp. and performing crosslinking so as to obtain a specific gel ratio.

Solution: An inflation film made of a high mol.wt. polyethylene having a thickness of 14 μm is produced. This film 31 is held between a pair of stainless steel mold frames 33 and four sides thereof are fixed between the upper and lower mold frames by using screws 32. In this state, the whole is immersed in a tank filled with heated paraffin oil. The film fixed to the mold frames is taken out of a heat treatment tank to be immersed in a tank filled with 1,3-dichloro-1,1,2,2,3-pentafluoropropane in this state. This film is taken out to be dried by air and the dried film is detached from the mold frames. The obtained film is perforated and irradiated with electron beam of 2 Mrad to perform crosslinking. This perforated film has a gel ratio of 59 and also has a closing temp. of 131°C and heat-resistance temp. of 175°C.

COPYRIGHT: (C)1999,JPO

► [See a clear and precise summary of the whole patent, in understandable terms.](#)

Family:


[Show known family members](#)

Other Abstract Info:

CHEMABS 131(18)244387W CHEMABS 131(18)244387W DERABS C1999-614756 DERABS C1999-614756

Foreign References:

No patents reference this one



[View Image](#)

1 page

BEST AVAILABLE COPY



Nominate this
for the Gallery...

[Subscribe](#) | [Privacy Policy](#) | [Terms & Conditions](#) | [FAQ](#) | [Site Map](#) | [Help](#) | [Contact Us](#)

© 1997 - 2002 Delphion Inc.

BEST AVAILABLE COPY



(19)

(11) Publication number: **11268118 A**

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **10106766**(51) Intl. Cl.: **B29C 55/28 B29C 35/08 B29C 67/20 H01M 2/16**(22) Application date: **16.04.98**(30) Priority: **26.01.98 JP 10 12711**(43) Date of application
publication: **05.10.99**(84) Designated contracting
states:(71) Applicant: **MITSUI CHEM INC**(72) Inventor: **HASHIMOTO AKINAO
MORISHIGE KOZO
YAGI KAZUO**

(74) Representative:

**(54) POLYOLEFIN POROUS
FILM, PRODUCTION
THEREOF, AND
SEPARATOR FILM FOR
BATTERY**

(57) Abstract:

PROBLEM TO BE SOLVED: To provide a film suitably used in a non-aqueous electrolyte and a separator for an electrolyte battery so as to have specific closing temp. and heat-resistant temp. and performing crosslinking so as to obtain a specific gel ratio.

SOLUTION: An inflation film made of a high mol.wt. polyethylene having a thickness of 14 μm is produced. This film 31 is held between a pair of stainless steel mold frames 33 and four sides thereof are fixed between the upper and lower mold frames by using screws 32. In this state, the whole is immersed in a tank filled with heated paraffin oil. The film fixed to the mold frames is taken out of a heat treatment tank to be immersed in a tank filled with 1,3-dichloro-1,1,2,2,3-

pentafluoropropane in this state. This film is taken out to be dried by air and the dried film is detached from the mold frames. The obtained film is perforated and irradiated with electron beam of 2 Mrad to perform crosslinking. This perforated film has a gel ratio of 59 and also has a closing temp. of 131°C and heat-resistance temp. of 175°C.

COPYRIGHT: (C)1999,JPO

